# Atria<sup>®</sup> 20mm Porcelain Tiles

Technical datasheet





## Atria® 20mm Porcelain Tiles Technical datasheet



Atria® Porcelain Tiles



FIND OUT MORE OR REQUEST A SAMPLE e: technical@raaft.co

w:raaft.co

## Atria® 20mm Porcelain Tiles Technical datasheet

### STONE

		PRODUCT CODE & SIZES					
RANGE	COLOUR	600x600	600x900	300x1200	600x1200		
	Millstone	402014	-	-	-		
Florence	Graphite	402013	-	-	-		
	Silver	402030	-	-	-		
	Fawn	408023	-	-	-		
N4 11	Ferro	408024	-	-	-		
Modica	Pewter	408025	-	-	-		
	Silver	415013	-	-	-		
	Cameo	-	461101	-	-		
N	Ember	-	461104	-	-		
Novara	Ashen	-	461107	-	-		
	Slate	-	461110	-	-		
	String	-	-	-	407024		
Modena	lvory	-	-	-	407023		
	Smoke	-	-	-	407025		
	Steel	-	-	-	408023		
Taranto	Hessian	-	-	-	408024		
	Charcoal	-	-	-	408025		
	Carbon	410010	-	-	410015		
	Mushroom	410011	-	-	410016		
Asti	Smoke	410012	-	-	410017		
	Talc	410013	-	-	410018		
	Taupe	410014	-	-	410019		
	Earth	404026	-	-	-		
Roma	Lead	404027	404037	404017	-		
Roma	Natural	404029	404041	404018	-		
	Copper	404025	-	-	-		
	Pearl	419005	-	-	419001		
Lucas	lvory	419006	-	-	419002		
Lucca	Beige	419007	-	-	419003		
	Grey	Add	419004				

### CONCRETE

RANGE	COLOUR	PRODUCT CODE & SIZES				
RANGE	COLOOR	600x600				
	Anthracite	406011				
Venice	Beige	406012				
Venice	Grey	406013				
	Mocha	406014				
	Cloud	416010				
Pavia	Ochre	416011				
Pavia	Urban	416012				
	Shadow	416013				

## TERRAZZO

PANCE	COLOUR	PRODUCT CODE & SIZES
RANGE	COLOUR	600x600
Padua	Thunder	417010

For LRV ratings please reach out to a member of the team.



FIND OUT MORE OR REQUEST A SAMPLE e: technical@raaft.co w:raaft.co

© 2024 Raaft® Ltd.

## Atria® 20mm Porcelain Tiles Technical datasheet

#### PACKAGING AND WEIGHTS

		BOX SPECIFICATION			PALLET SPECIFICATION		
TILE SIZE	THICKNESS	PIECES/ BOX	SQM/ BOX	Kg/ BOX	TILES/ PALLET	SQM/ PALLET	Kg/ PALLET
225 x 225	20mm	12	0.720	≅67.54	45	51.84	≅1034.82
225 x 454	20mm	6	0.810	≅37.99	42	14.58	≅810.43
300 x 600	20mm	3	0.720	≅25.33	40	8.10	<b>≅</b> 506.52
300 x 1200	20mm	2	0.720	≅26.38	36	16.88	≅1519.56
600 x 600	20mm	2	0.563	≅50.65	30	45.36	≅5673.02
450 x 900	20mm	2	0.960	≅33.77	27	17.28	≅810.43
400 x 1200	20mm	2	0.720	≅33.77	24	25.92	≌949.73
600 x 900	20mm	2	2.880	≅28.49	18	5.47	≅303.91
750 x 750	20mm	1	1.080	≅135.07	42	51.84	<b>≅</b> 512.85
600 x 1200	20mm	1	0.540	≅33.77	15	28.80	≅1013.04
300 x 2400	20mm	1	1.440	≅28.75	36	12.26	≅759.78
900 x 900	20mm	1	0.810	≅45.02	18	25.92	≌911.74
1200 x 1200	20mm	1	0.613	≅39.99	20	34.02	≅1595.54
1200 x 2400	20mm	1	0.608	≅33.77	9	32.40	≅3039.12

#### SLIP RESISTANCE

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED	ATRIA® VALUES
Dynamic slider	BCRA	Test method available	>0.4
Static slider	ASTM C1028	Test method available	-
Inclined platform	DIN 51130	Test method available	RII
Pendulum test value (PTV) - dry	BS EN 14231	36+	72
Pendumul test value (PTV) - wet	BS EN 14231	36+	65

#### WORKING SIZE AND WEIGHT

TILE SIZE	ACTUAL RECTIFIED SIZE	M2/TILE	KG/TILE
600 x 600	596 x 596	0.3600	≤16.88
600 x 900	596 x 1195	0.5400	≤25.33
300 x 1200	297 x 1195	0.3600	≤16.88
600 x 1200	596 x 1195	0.7200	≤33.77



#### FIND OUT MORE OR REQUEST A SAMPLE

e: technical@raaft.co w:raaft.co

© 2024 Raaft® Ltd.

## Atria® 20mm Porcelain Tiles Technical datasheet

#### **REGULARITY CHARACTERISTICS**

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED		ATRIA® VALUES
Length and width	ISO 0545-2	±0.6%	±2mm	≥3400N
Thickness	ISO 0545-2	±5.0%	±0.5mm	≥2720N
Squareness	ISO 0545-2	±0.5%	±2mm	≤l.8mm
Straightness of sides	ISO 0545-2	±0.5%	±1.5mm	≥13mm
Surface fitness	ISO 0545-2	±0.5%	±2mm	≤7.0%

#### STRUCTURAL CHARACTERISTICS

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED	ATRIA® VALUES	
	ISO 0545-3	±0.5%	±0.1%	
Water absorption	ASTM C373		In accordance	
Breaking strength	ISO 0545-4	≥1300N	≥7,288N	
Modulus of rupture	ISO 0545-4	≥35mm³	≥45 N/mm³	
Breaking load class	EN1339	±0.5%	UII TII	

#### SURFACE CHARACTERISTICS

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED	ATRIA® VALUES
Resistance to deep abrasion	ISO 0545-6	≤175mm³	≤155mm³

#### THERMAL AND HYGROMETRIC CHARACTERISTICS

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED	ATRIA® VALUES
Coefficient of linear thermal expansion	ISO 0545-8	Test method available	<7 x 10-6 °C-1
Thermal shock resistance	ISO 0545-9	Test method available	Guaranteed
Frost resistance	ISO 0545-12	Required	In accordance

#### CHEMICAL CHARACTERISTICS

TECHNICAL FEATURES	SPECIFICATION	VALUES REQUIRED	ATRIA <sup>®</sup> VALUES
Chemical resistance	ISO 0545-13	Test method available	Guaranteed
Stain resistance	ISO 0545-14	Test method available	Guaranteed



#### FIND OUT MORE OR REQUEST A SAMPLE

e: technical@raaft.co w:raaft.co

#### © 2024 Raaft® Ltd.

## Atria® 20mm Porcelain Tiles Technical datasheet

## APPLICATION

By mounting on adjustable pedestal systems or solid concrete bases. If mounting on adjustable pedestals over 100mm in height, an optional fiberglass mesh is available upon request.

## INSTALLATION INFORMATION

By mounting on adjustable pedestal systems or solid concrete bases. If mounted on adjustable pedestals over 100mm in height, an optional fibreglass mesh is available upon request.

## HOW RAAFT® OVERCOMES WIND UPLIFT WITH ATRIA® PORCELAIN TILES

To overcome uplift challenges on roof terraces, Raaft® has developed wind uplift resistance tiles. Products that claim to be resistant to wind uplift must meet BS EN 1991-1-4:2005++A1:2010 Eurocode 1 regulations, so we put out tiles and clips to the test. Following hte principles of BS 14437:2004, the tests were conducted by independent testers (BRE Group) on both types of clip, fixing 20mm thick Atria® + Porcelain tiles with two clips per tile attaching them to the Raaft® Aluminium Joists. Tests were also carried out on the Pedestal Joist Connectors.

Testing applied an uplift pressure of 4536N/m2 and the products were tested to destruction, no partial safety factors were used

The results were as follows:

- Using stainless steel clips, the characteristic wind uplift resistance per clip was 738.1N
- Using nylon clips the characteristic wind uplift per clip was 51.6N
- By also fixing the tile with Formoa 017FE hybrid polymer adhesive the indicative wind uplift resistance per clip was 2943N
- The pedestal joist connector returned a wind uplift resistance of 71.0

The clip and groove wind uplift resistance system is also featured on our Terrafina Composite. Wood polymer Decking and Farrino Porcelain Decking

Wind uplift clip



To view the full BRE Report, please visit raaft.co/storage/uploads/wind-uplift-test-bre-report\_kwbro.pdf



FIND OUT MORE OR REQUEST A SAMPLE e: technical@raaft.co w:raaft.co

© 2024 Raaft® Ltd.

## Atria® 20mm Porcelain Tiles Technical datasheet

### **PRODUCT FINISHES**

STONE					STONE	(CONT	INUED)		
FLORENCE	Graphite	Silver			ROMA Earth	Lead	Natural	Copper	
MODICA	Ferro	Pewter	Silver		ASTI Carbon	Mushroom	Smoke	Talc	Taupe
NOVARA	R ASSAULT OF MANY				CONC	DETE			
	Sal Ca		1 spells		CONC	REIE			
					VENICE				
Cameo	Ember	Ashen	Slate						
MODENA					Anthracite	Beige	Grey	Mocha	
- marine									
					PAVIA				
String	lvory	Smoke							
TARANTO					Cloud	Ochre	Urban	Shadow	
144									
Charl		Changel			TERAZ	ZO			
Steel	Hessian	Charcoal			PADUA				
LUCCA									
					Thunder				
Devel	Deine	Carrie			monder				
Pearl	Beige	Grey	lvory						
<b>२</b> R/	<b>AAFT</b>	FIND OUT M e: technical@ w:raaft.co		UEST A SAMPLE					

## Atria® 20mm Porcelain Tiles Technical datasheet

### **SUSTAINABILITY**

Atria® porcelain tiles are made by pressing and baking a mix of natural minerals and clays. This process creates strong and long-lasting tiles. Unlike many other materials, these tiles are eco-friendly. They don't soak up harmful chemicals or release contaminants. They're also easy to clean without needing strong chemicals.

### **PRODUCT MAINTENANCE**

Our Atria® tiles are easy to clean and resist most chemicals. They're UV stable and only have 0.01% porosity. It's a good idea to clean them once or twice a year, depending on local weather conditions. Use a high-pressure cleaner from at least 20cm away or scrub with a mild all-purpose cleaner and water. For daily cleaning, just sweep regularly and rinse with water, a soft brush, and a mild cleaner or suds.

### FIRE PROTECTION

By mounting on adjustable pedestal systems or solid concrete bases. If mounted on adjustable pedestals over 100mm in height, an optional fibreglass mesh is available upon request.

### PROTECTIVE EQUIPMENT

By mounting on adjustable pedestal systems or solid concrete bases. If mounted on adjustable pedestals over 100mm in height, an optional fibreglass mesh is available upon request.

- a) Good strong safety boots/shoes to protect the feet.
- b) Protective eyewear such as safety glasses.
- c) Strong gloves to protect the hands.
- d) If using loud cutting equipment then ear plugs or defenders should be worn.

## STORAGE AND HANDLING

In preparation for delivery, Atria® tiles are securely packed into cardboard boxes to ensure no movement during transit.

Depending on the size and weight of the consignment they may be palletised. Until the point of installation, the tiles should be stored fully packed in a dry environment.



FIND OUT MORE OR REQUEST A SAMPLE e: technical@raaft.co

© 2024 Raaft® Ltd.

At the time of writing and publication of the sheet, all information is specified correctly. The company reserves the right to change the specifications of this product at any time without prior notice to third parties. Any images and diagrams used in this sheet are intended only as illustrations. No rights can be derived from them.

w raaft co

## Atria® 20mm Porcelain Tiles Technical datasheet

### ACCESSORIES

#### VENICE CLIP

The genesis of our product stemmed from valuable feedback received from a domestic building grappling with water pooling issues on their porcelain tiles. After meticulous contemplation and design efforts spanning several months, the solution was crafted.

The predicament of water pooling takes on greater significance with the introduction of new materials to the UK market. Despite tiles boasting ratings of R11 or higher, the accumulation of water transforms into ice during winter, prompting the exclusion of porcelain from specifications on roof terraces nationwide.

Enter our innovative product, poised to address this challenge effectively. Raaft® now offers a solution enabling water drainage from tiles within a precise 1-hour timeframe, aligning seamlessly with NHBC 9.1.15 guidelines. According to these standards, standing water post-rain should neither exceed 5mm in depth nor cover an area surpassing 1m<sup>2</sup>. We prioritize subtlety, employing transparent materials potentially matching Raaft®'s specified tiles. The Venice clip is designed to break the surface tension of the tile, similar to a grout joint where porcelain tiles are installed on cement. When porcelain is installed onto a loose laid system the joints are exposed which meant the files fill with water due to surface tension.

The product is flush to the surface reducing the chances of feet being caught.

During installation, especially in wind uplift scenarios, our design incorporates a clip securely inserted into the groove. This not only ensures a snug fit but also acts as a protective 'buffer' between tiles, facilitating removal and reinstallation without compromising structural integrity.



Venice Clip Push – this item serves as a universal solution for all porcelain within the RAAFT® collection.



Venice Clip Uplift



FIND OUT MORE OR REQUEST A SAMPLE e: technical@raaft.co w:raaft.co

© 2024 Raaft® Ltd.